


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 8/04, 8/12	A1	(11) International Publication Number: WO 97/48144 (43) International Publication Date: 18 December 1997 (18.12.97)
(21) International Application Number: PCT/GB97/01566 (22) International Filing Date: 11 June 1997 (11.06.97) (30) Priority Data: 9612389.8 13 June 1996 (13.06.96) GB (71) Applicant (for all designated States except US): KEELE UNIVERSITY [GB/GB]; Keele, Staffordshire ST5 5BG (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): KENDALL, Kevin [GB/GB]; Wycherley, Tower Road, Ashley Heath, Market Drayton, Shropshire TF9 4PY (GB). KILBRIDE, Ian [GB/GB]; 2 Sunnydale Crescent, Hinkley, Leicestershire LE10 0PA (GB). (74) Agent: ALLMAN, Peter, John; Marks & Clerk, Sussex House, 83-85 Mosley Street, Manchester M2 3LG (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FUEL CELL POWER GENERATING SYSTEM (57) Abstract <p>A small scale ceramic fuel cell system to which fuel gas (2) is supplied through an injector (5) which draws ambient air into the system. The air/fuel gas mixture is passed through a catalytic oxidation device (8) which is thereby heated and heats a fuel cell (9). Air and fuel gas react at the fuel cell to generate an electrical output.</p> 		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

FUEL CELL POWER GENERATING SYSTEM

The present invention relates to an electrical power source.

There are many circumstances in which it is necessary to be able to power electrical equipment for which there is no ready access to a mains power supply. For example power supplies are required for communications equipment, electronic sensors and other devices, small motors and lights. Such devices typically require milliwatts or decawatts of power and in the past the only option in such circumstances has been the use of electrical batteries. Batteries require regular replacement which is a major disadvantage associated with their use.

Electronic sensors comprising ceramic electrolytes with electrodes made of platinum are known. Unfortunately, typically they produce only microwatts of power which is too small in many applications.

It is an object of the present invention to provide a fuel cell system suitable for replacing batteries as an electrical power source.

According to the present invention, there is provided an electrical power source comprising a fuel gas supply, means for delivering an air/fuel gas mixture to a catalytic oxidation device such that the catalytic oxidation device is heated by oxidation of fuel gas, a fuel cell located so as to be heated as a result of the heating of the catalytic oxidation device, and means for delivering air and fuel gas to the fuel cell, the fuel cell when heated and supplied with air and fuel generating an electrical output.

The power source may be supplied with fuel gas from a bottle or any other available source of fuel gas. The fuel gas supply may be connected to an injector arranged to draw ambient air into a conduit connected to the catalytic oxidation device, the air and fuel gas being mixed in the conduit. Preferably the catalytic oxidation device is connected in series with and upstream of the fuel cell in the conduit.

A further catalytic oxidation device may be provided downstream of the fuel cell to consume any residual fuel gas. The fuel cell may be defined by one or more ceramic tubes through which the fuel gas flows. Such tubes may be formed from zirconium oxide doped with yttria. The or each catalytic oxidation device may be formed from a porous mass of ceramic fibres supporting a platinum catalyst.

A sulphur absorbent filter may be provided upstream of the catalytic oxidation device, and the catalytic oxidation device and fuel cell may be located within a thermally insulating jacket.

An embodiment of the present invention will now be described, by way of example, with reference to the accompanying drawing.

The drawing is a schematic representation of an embodiment of the invention which is capable of providing an output voltage of 0.5 volts and an output current of 30mA. Fuel gas is supplied via a pipe 1 as indicated by arrow 2 from a bottle (not shown) of LPG or LNG. It will be appreciated that any gaseous hydrocarbon fuel could be used. The supply of gas is controlled by a

valve 3 such that when the valve is open gas passes through a filter 4 and injector 5 into a conduit 6. The filter removes undesirable components such as sulphur which might disrupt the operation of the device. The filter may be for example a plug of glass fibre incorporating a molybdenum or other pellet capable of absorbing sulphur from the gas.

An aperture 7 is formed in the conduit 6. A fuel gas stream issuing from the injector 5 creates a venturi effect and therefore draws a controlled amount of ambient air into the conduit 6 through the aperture 7. The air and fuel gas is mixed within the conduit and then passes through a porous plug 8 of high surface area ceramic containing platinum catalyst. The fuel gas and air mixture reacts and as a result the plug 8 is heated, heating the gas passing through it and the remainder of the device. The plug 8, aperture 7 and the fuel gas flow rate are selected such that the gas emerging from the plug 8 is substantially free of oxygen.

The heated gas passes from the plug 8 into a pair of ceramic fuel cell tubes 9 connected to terminals 10. The tubes 9 and the portion of the conduit incorporating the catalyst plug 8 are located within an open-ended housing defined by an insulating body 11. Thus the rate at which heat leaks from the system is limited but the space defined within the insulated housing 11 is sufficient to enable air to diffuse readily into the region around the tubes 9. Thus the tubes are maintained at a temperature sufficient for them to operate as fuel

cells and a voltage is developed as a result of the electrochemical reaction between fuel gas within the tubes 9 and oxygen in the region around the tubes 9.

A further plug 12 of high surface area platinum-containing ceramic is positioned adjacent the open end of the tubes 9 such that any residual fuel gas emerging from the tubes 9 is further reacted. Thus substantially no fuel gas leaks from the assembly.

It will be appreciated that in the described device the assembly is self-heating to the required operating temperature for fuel cell operation and therefore does not require a separate heat source for establishing its operation. Furthermore it is not necessary to provide any external power supply nor supply pressurised air or oxygen.

The tubes 9 may be of the type described in International Patent Application No. GB94/00549. The preferred ceramic is zirconium oxide, doped with yttria to provide good ionic conductivity. However, other ceramic electrolytes can be used, including those containing ceria, gadolinia, and other oxide materials. Furthermore, other dopants could be used including scandia, magnesia and calcia. Several types of electrode and current collectors structures may be used for the tubes, for example one of those described in the above mentioned International Patent Application. Platinum is the preferred material for the electrodes because of its long lifetime, but alloys of platinum and other metals may be used. Gold and silver alloys are satisfactory under certain conditions. Perovskites such as lanthanum, strontium, manganite may be used

on cathode surfaces defined by the tubes to improve performance. Lanthanum strontium chromite or other stable oxides may be used on anode electrode surfaces to improve performance.

The catalyst material used to define the plugs 8 and 12 could be made from high surface area saffil alumina fibre loaded with 5% by weight of platinum deposited from chloroplatinic acid. Alternatively, a metal mesh may be coated with platinum black to give a catalytic effect.

The filter 5 which removes potentially disruptive sulphur from the gas stream may be made of glass fibre incorporating molybdenum or other suitable pellets.


An example of the device illustrated in the accompanying drawing was prepared by impregnating saffil catalyst grade alumina fibre with H_2PtCl_6 equivalent to 5% by weight of platinum. This was dried and heated in a reducing atmosphere to 600°C . 1g of this catalyst material was rolled between metal meshes to form a tube which was placed in an alumina support tube. Natural gas was passed through an injector to draw air into the tube. The catalyst became hot and stabilised at 700°C . A zirconia fuel cell tube with Ag/Pd anode and lanthanum strontium manganite cathodes with silver wire current collectors was inserted into the hot zone downstream of the heated catalyst and was fed with natural gas. The fuel cell produced 0.5Volts at 30mA.

CLAIMS

1. An electrical power source comprising a fuel gas supply, means for delivering an air/fuel gas mixture to a catalytic oxidation device such that the catalytic oxidation device is heated by oxidation of fuel gas, a fuel cell located so as to be heated as a result of the heating of the catalytic oxidation device, and means for delivering air and fuel gas to the fuel cell, the fuel cell when heated and supplied with an air/fuel mixture generating an electrical output.
2. A power source according to claim 1, wherein the fuel gas supply is connected to an injector arranged to draw ambient air into a conduit connected to the catalytic oxidation device, the air and fuel gas being mixed in the conduit.
3. A power source according to claim 1 or 2, wherein the catalytic oxidation device is connected in series with and upstream of the fuel cell.
4. A power source according to claim 3, wherein a further catalytic oxidation device is provided downstream of the fuel cell.

5. A power source according to any preceding claim, wherein the fuel cell is defined by at least one ceramic tube.
6. A power source according to claim 5, wherein the or each tube is formed from zirconia oxide doped with yttria.
7. A power source according to any preceding claim, comprising a catalytic oxidation device formed from a porous mass of ceramic fibres supporting a platinum catalyst.
8. A power source according to any preceding claim, comprising a sulphur absorbent filter upstream of the catalytic oxidation device.
9. A power source according to any preceding claim, wherein the catalytic oxidation device and the fuel cell are housed within a thermally insulating jacket.
10. A power source substantially as hereinbefore described with reference to the accompanying drawing.

1-1



INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/01566

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 H01M8/04 H01M8/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 668 622 A (ROLLS ROYCE PLC) 23 August 1995 see column 13, line 17 - column 14, line 6; figure 1 see column 12, line 27 - line 41	1-3,7-10
Y	---	2,5,6
X	PATENT ABSTRACTS OF JAPAN vol. 009, no. 185 (E-332), 31 July 1985 & JP 60 054178 A (MATSUSHITA DENKI SANGYO KK), 28 March 1985, see abstract	1,7,10
Y	& CHEMICAL ABSTRACTS, vol. 103, no. 10, 9 September 1985 Columbus, Ohio, US; abstract no. 73879, see abstract ---	2,5,6
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

23 September 1997

Date of mailing of the international search report

08.10.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

D'hondt, J

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 97/01566

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 718 506 A (FISCHER W ET AL) 27 February 1973 see column 3, line 48 - line 52; figure 1 see column 4, line 38 - column 5, line 10	1,4,9,10
Y	---	2,5,6
X	PATENT ABSTRACTS OF JAPAN vol. 012, no. 493 (E-697), 22 December 1988 & JP 63 205058 A (MITSUBISHI ELECTRIC CORP), 24 August 1988, see abstract	1,10
Y	---	2,5,6
X	PATENT ABSTRACTS OF JAPAN vol. 013, no. 016 (E-703), 13 January 1989 & JP 63 224157 A (MITSUBISHI ELECTRIC CORP), 19 September 1988, see abstract	1,10
Y	---	2,5,6
Y	US 3 486 943 A (WIDELL MARJA) 30 December 1969 see column 2, line 37 - line 49; claims 1-4; figure 1	5,6
Y	---	2
Y	EP 0 486 911 A (DESSAU GASGERAETE GMBH) 27 May 1992 see column 4, line 20 - line 36; claim 1; figure 2	
X	---	1,10
X	PATENT ABSTRACTS OF JAPAN vol. 007, no. 229 (E-203), 12 October 1983 & JP 58 119168 A (TOKYO SHIBAURA DENKI KK), 15 July 1983, see abstract & CHEMICAL ABSTRACTS, vol. 100, no. 2, 9 January 1984 Columbus, Ohio, US; abstract no. 10027, see abstract	
X	---	1,4,9,10
	PATENT ABSTRACTS OF JAPAN vol. 012, no. 500 (E-699), 27 December 1988 & JP 63 211573 A (MITSUBISHI HEAVY IND LTD), 2 September 1988, see abstract & CHEMICAL ABSTRACTS, vol. 110, no. 8, 20 February 1989 Columbus, Ohio, US; abstract no. 61101, see abstract	

	-/--	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 97/01566

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 095, no. 010, 30 November 1995 & JP 07 169476 A (TOSHIBA CORP), 4 July 1995, see abstract & DATABASE WPI Derwent Publications Ltd., London, GB; AN 95-267023 see abstract ---	1,10
P,X	DATABASE WPI Section Ch, Week 9724 Derwent Publications Ltd., London, GB; Class J04, AN 97-265003 XP002041560 & JP 09 092 311 A (SANYO ELECTRIC CO LTD) , 4 April 1997 see abstract & CHEMICAL ABSTRACTS, vol. 127, no. 2, 14 July 1997 Columbus, Ohio, US; abstract no. 20922, see abstract ---	1,3,9,10
A	DE 35 03 003 A (VOGEL RAINER DR) 9 October 1986 see claim 1; figure 3 ---	1
P,A	WO 96 29751 A (LOCKHEED IDAHO TECHNOLOGIES CO) 26 September 1996 see claim 1; figures 1,2 -----	1,10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 97/01566

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0668622 A	23-08-95	CA 2142755 A JP 7272743 A US 5554454 A	20-08-95 20-10-95 10-09-96
US 3718506 A	27-02-73	NONE	
US 3486943 A	30-12-69	SE 311678 B FR 1515563 A NL 6704337 A	23-06-69 17-06-68 26-09-67
EP 0486911 A	27-05-92	DE 4036823 A DE 59106725 D	21-05-92 23-11-95
DE 3503003 A	09-10-86	NONE	
WO 9629751 A	26-09-96	US 5641585 A AU 5319496 A	24-06-97 08-10-96